



LOMAX COPY PAPER 80GSM

Parameters	Standard	Unit	Measurement
Substance	ISO 536	g/m ²	80 +/- 3
Thickness	ISO 534	µm	106 +/- 3
Bulk	ISO 534		1,32
Moisture Content	ISO 287	%	4,3 +/- 0,7
Roughness	ISO 8791	Bendtsen ml/min	200 +/- 50
Whiteness	ISO 11475	CIE	153 +/- 3
Brightness D65	ISO 2470-2	%	107 +/- 2
Opacity	ISO 2471	%	93 +2/-1
Stiffness MD	ISO 2493	mN	110 +/- 15
Stiffness CD	ISO 2493	mN	55 +/- 15



References:
 Product is made taking into account requirements of DIN EN 12281
 Product made from ECF Pulp
 ISO 45001 - Health & Safety

The data presented can be changed without notice.

Technical Data Sheet

Production sites:

The production mills operate in compliance with the following standards



Special Attributes:

